

TechKote WA2951F (SP-1) Water-Based Coating

Black, Corrosion Resistant, High Heat, Low VOC, Water Based

DESCRIPTION:

TechKote 2951F (SP-1) Series, available in multiple colors, is a low gloss, durable, water-based rust preventive coating, adaptable for spray application or roller applications on various substrates including metal, wood, rubber and asphalt shingles. This quality product is a complete water-based coating designed to protect metal substrates even when applied at low film builds. The coating is fast-drying, can be air-dried or force-dried and does not need high temperature bake cycles. **WA2951 F (SP-1)** does not contribute significantly to VOC emissions, nor does it contain any heavy metals.

TYPICAL PROPERTIES (NOT SPECIFICATIONS):

Appearance	Liquid (Colored to Requirement)
Viscosity	500-1500 cPs
Density (lbs/gal)	10.0
Non-Volatile Solids By Weight	20.0 - 45.0%
Volatile Organic Compounds (calculated)	0.011 lbs/gal

FEATURES / BENEFITS:

- Water based , Low VOC

MIX / APPLICATION & USE:

Mix completely before use. TechKote WA 2951 F (SP-1) typically is applied at a minimum film thickness of 2.5 mils (unless otherwise directed by the customer approval). TechKote WA 2951 F (SP-1) is an air-dry coating, however, to reduce dry time, it may be oven dried as long as part temperature does not exceed 180 degrees Fahrenheit.

TechKote WA2951F (SP-1) Water-Based Coating

Black, Corrosion Resistant, High Heat, Low VOC, Water Based

HEALTH & SAFETY:

TechKote WA 2951 F (SP-1) Series is available at our Brighton, Michigan facility in 55-gallon drums, 330 or 275-gallon totes and 5-gallon pails.

Storage And Handling: See Safety Data Sheet Before Use.

Do not freeze. Store at temperature between 45-100 degrees Fahrenheit. Do not pressurize container or reuse empty container.

Non-Warranty: While the information and recommendations sent forth herein are believed to be accurate as of the date thereof, Fortech Products, Inc. makes no warranty with respect thereto and disclaims all liability for reliance therein.

Last Updated: 07/01/2024